

Appl. No. 10/702,181
Amendt. dated January 26, 2006
Reply to Advisory Action of January 18, 2006

Amendment to the Claims:

This listing of claims will replace all prior versions and listings of claims in the application.

Listing of Claims:

Please cancel claim 8.

Claim 1 (previously presented): A performance enhancing break-in method for a proton exchange membrane fuel cell (12), the fuel cell including an anode electrode (14) and a cathode electrode (16) secured to opposed sides of a proton exchange membrane electrolyte (18), the method comprising the steps of:

5 a. cycling a potential of the anode electrode (14) for a first electrode cycle by changing the potential of the selected electrode (14, 16) within a potential range of between 0.00 volts to 1.20 volts from a first potential within the range to a second potential within the range and then changing the potential of the selected electrode (14, 16) from the second potential back to the first potential while exposing the anode electrode (14) to an inert gas and while exposing the cathode electrode (16) to a gas selected from the group consisting of a hydrogen containing gas, a reducing fluid reactant, and a mixture of a reducing fluid and an inert gas by lowering the potential of the anode electrode (14) within the potential range by first exposing the anode electrode

10

15

20

Appl. No. 10/702,181
Amendt. dated January 26, 2006
Reply to Advisory Action of January 18, 2006

(14) to the inert gas while exposing the cathode electrode (16) to the reducing fluid reactant, and then raising the potential of the anode electrode (14) within the potential range by exposing the anode electrode (16) to an oxidant reactant while continuing to expose the cathode electrode (16) to the reducing fluid reactant; and,

- b. repeating the cycling of the potential of the anode electrode (14, 16) for at least a second electrode cycle.

Claim 2 (canceled)

Claim 3 (canceled)

Claim 4 (canceled)

Claim 5 (currently amended): A performance enhancing break-in method for a proton exchange membrane fuel cell (12), the fuel cell including an anode electrode (14) and a cathode electrode (16) secured to opposed sides of a proton exchange membrane electrolyte (18), the method comprising the steps of:

- a. cycling a potential of the cathode electrode (16) for a first cathode cycle by changing the potential of the cathode electrode (16) within a potential range of between 0.00 volts to 1.20 volts from a first cathode potential within the range to a second cathode potential within the range and then changing the potential of the cathode electrode (16) from the second cathode potential back to the first cathode

Appl. No. 10/702,181

Amendt. dated January 26, 2006

Reply to Advisory Action of January 18, 2006

15 potential while exposing the cathode electrode (16) to
an inert gas and while exposing the anode electrode
(14) to a gas selected from the group consisting of a
hydrogen containing gas, a reducing fluid reactant,
and a mixture of a reducing fluid and an inert gas;
20 b. repeating the cycling of the potential of the cathode
electrode (16) for at least a second cathode cycle;
c. cycling a potential of the anode electrode (14) for a
first anode cycle by changing the potential of the
anode electrode (14) from a first anode potential
within the potential range of between 0.00 volts to
25 1.20 volts to a second anode potential within the
range and then changing the potential of the anode
electrode (14) from the second anode potential back to
the first anode potential while exposing the anode
electrode (14) to an inert gas and while exposing the
30 cathode electrode (16) to a gas selected from the
group consisting of a hydrogen containing gas, a
reducing fluid reactant, and a mixture of a reducing
fluid and an inert gas by lowering the potential of
the anode electrode (14) within the potential range by
35 first exposing the anode electrode (14) to the inert
gas while exposing the cathode electrode (16) to the
reducing fluid reactant, and then raising the
potential of the anode electrode (14) within the
potential range by exposing the anode electrode (14)
40 to an oxidant reactant while continuing to expose the
cathode electrode (16) to the reducing fluid reactant;
and,

Appl. No. 10/702,181

Amendt. dated January 26, 2006

Reply to Advisory Action of January 18, 2006

-
- d. repeating the cycling of the potential of the anode electrode (14) for at least a second anode cycle.

Claim 6 (original) The method of claim 5, comprising the further steps of cycling the potential of the cathode electrode (16) by applying a direct electrical current to the cathode electrode (16) from a programmable direct current power source (80) to change the potential of the cathode electrode (16) from the first potential to the second potential, and then to change the potential of the cathode electrode (16) back to the first potential, and cycling the potential of the anode electrode (14) by applying a direct electrical current to the anode electrode (14) from the programmable direct current power source (80) to change the potential of the anode electrode (14) from the first potential to the second potential, and then to change the potential of the electrode (14) back to the first potential.

Claim 7 (previously presented): The method of claim 5 further comprising the steps of cycling the potential of the cathode electrode (16) by lowering the potential of the cathode electrode (16) within the potential range by first exposing the cathode electrode (16) to the inert gas while exposing the anode electrode (14) to the reducing fluid reactant, and then raising the potential of the cathode electrode (16) within the potential range by exposing the cathode electrode (16) to an oxidant reactant while continuing to expose the anode electrode (14) to the reducing fluid reactant.

Claim 8 (canceled)

Appl. No. 10/702,181

Amendt. Dated, December 30, 2005

Reply to Office Action of October 28, 2005

5 Claim 9 (previously presented): The method of claim 5, further comprising the steps of, after the cycling the potential of the cathode electrode (16) step and the cycling the potential of the anode electrode (14) step, calibrating performance of the fuel cell (12) by a performance calibration step by exposing the anode electrode (14) to the reducing fluid reactant and exposing the cathode electrode (16) to an oxidant reactant, then closing a primary load switch (78) to connect a primary load (74) to the anode and cathode electrodes (14, 16) for a predetermined
10 duration, then opening the primary load switch (78) after the duration, and then repeating the performance calibration step a predetermined number of repetitions.

Claim 10 (canceled)

Claim 11 (canceled)